

Technical Data Sheet

Polystone[®] G B 100 black extruded

PE-HD (PE 100)

Typical characteristics

- Chemical resistant
- Suitable for contact with drinking water

Typical industries

- Chemical Processing Industry
- Chemical storage tanks

Sustainability

- LCA available (ISO 14040/44)

| | Test method | Unit | Guideline value |
|--|-------------------------|----------------------|-------------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | >0,96 |
| Water absorption | DIN EN ISO 62 | % | <0,01 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Moulding Compound PE | ISO 17855-1 | | PE,,EACH,62,T003 |
| Mechanical properties | | | |
| Yield stress | DIN EN ISO 527 | MPa | >23 |
| Elongation at break | DIN EN ISO 527 | % | >50 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >1100 |
| Notched impact strength | DIN EN ISO 179 | kJ / m ² | >16 |
| Shore hardness | DIN EN ISO 868 | scale D | 63 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 130 ... 135 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,40 |
| Thermal capacity | DIN 52612 | kJ / (kg * K) | 1,90 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 150 ... 230 |
| Service temperature, long term | Average | °C | -50 ... 80 |
| Service temperature, short term (max.) | Average | °C | 100 |
| Vicat softening temperature | DIN EN ISO 306, Vicat B | °C | 67 |
| Electrical properties | | | |
| Dielectric constant | IEC 60250 | | 2,5 |
| Dielectric dissipation factor (10 ⁶ Hz) | IEC 60250 | | 0,0004 |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | >10 ¹⁴ |

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



| | Test method | Unit | Guideline value |
|----------------------------|------------------|----------|-----------------|
| Surface resistivity | DIN EN 62631-3-2 | Ω | $>10^{14}$ |
| Comparative tracking index | IEC 60112 | | 600 |
| Dielectric strength | IEC 60243 | kV / mm | 45 |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (*) literature values



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 16/06/2026 • Release: 17/03/2026 • Version: 4.0
PIM-ID: 590982 • PIM-Code: 1226-29-33.12-9.7-3-4
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

