

Technical Data Sheet

Polystone[®] D Natural - ASTM

PE-HD / PE 500

Typical characteristics

- Good mechanical properties
- Good wear resistance
- Good cutting resistance
- High scratch resistance
- Good sliding properties

Typical industries

- Mechanical Engineering Industry
- Food Industry
- Bakery and Confectionery

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0.94
Carbon Black Content	ISO6964	%	n/a
Mechanical properties			
Hardness	ASTM D2240	Shore D	63-69
Flexural Modulus	ASTM D790	psi	150000
Izod Impact Strength	D4020		9
Thermal properties			
Melting Point		°F	275-280
Maximum Service Temperature, Air		°F	180
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁴	1.9

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 31/05/2024 • Version: 1.0
 PIM-ID: 717983 • PIM-Code: 40-18-17.143.9.23.223-5.5.5
 Company-IDs: 23070

Page 1 / 1 (Dates in DD/MM/YYYY)

