

## Technical Data Sheet

# SustaPEEK CM CF 30 - ASTM

PEEK

### Typical characteristics

- Flame retardant
- Self-extinguishing
- Low smoke density
- Good dimensional stability

### Typical industries

- Semiconductor Industry
- Electronics
- Oil and Gas
- Semiconductor Wafer Handling
- Semiconductor High and low temperature
- Semiconductor Dicing

	Test method	Unit	Guideline value
<b>General properties</b>			
Moisture	ASTM D6980	%	0.1
<b>Mechanical properties</b>			
Tensile Strength	ASTM D638	psi	13866
Tensile Modulus	ASTM D638	ksi	1297
Elongation at Break	ASTM D638	%	1.3
Flexural Strength	ASTM D790	psi	23634
Flexural Modulus	ASTM D790	ksi	1310

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Release: 01/03/2024 • Version: 1.0  
 PIM-ID: 752186 • PIM-Code: 30-16-16.12.15.153-11.8.5.15.5.7  
 Company-IDs: 23070

Page 1 / 1 (Dates in DD/MM/YYYY)

