

## Technical Data Sheet

# Trovidur<sup>®</sup> ET transparent

PVC-U

### Typical characteristics

- Alta transparencia
- Muy bueno imprimible
- RoHS
- Compatible con ELV
- Cumple con WEEE
- Compatible con RLAP
- Retardante de llama
- Autoextinguible tras retirar la llama.
- Baja absorción de humedad
- Resistencia química
- Aislamiento eléctrico
- Buena soldabilidad
- Buena termoformabilidad
- Good glueability
- Buena resistencia al impacto

### Typical industries

- Construcción de máquinas e instalaciones
- Construcción de contenedores químico

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,40
Water absorption	DIN EN ISO 62	%	0,20
Flammability (Thickness from 2 mm)	UL 94		V0
Flammability (Thickness 1 mm ... 5 mm)	NF P 92-501		M1
Flammability (Thickness 1 mm ... 5 mm)	DIN 4102		B1
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	70
Elongation at break	DIN EN ISO 527	%	10
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3200
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	2
Shore hardness	DIN EN ISO 868	scale D	83
Ball Hardness	ISO 2039	MPa	140

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 25/06/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 590990 • PIM-Code: 1088-26-13.14.14.16.15.16.16.11.12.33.13.16.34.3.162-5.9-5  
 Company-IDs: 20000-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Bending strength	DIN EN ISO 178	MPa	80
<b>Thermal properties</b>			
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	67
Service Temperature		°C	-10 ... +50
Heat deflection temperature	DIN EN ISO 75	°C	59
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>15</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	>10 <sup>13</sup>
Dielectric strength	IEC 60243	kV / mm	12
Comparative tracking index	IEC 60112	CTI	450

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 25/06/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 590990 • PIM-Code: 1088-26-13.14.14.16.15.16.16.11.12.33.13.16.34.3.162-5.9-5  
 Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

