

Technical Data Sheet

Maywoflamm[®] ECE PC/ABS

ABS

Typical characteristics

- Retardante de llama

Typical industries

- Construcción de vehículos
- Autobuses
- Tecnología de embutición profunda

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,19
Flammability	ECE R118		Annex 6, 7, 8 (1,5-6,0mm)
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	59
Elongation at yield stress	DIN EN ISO 527	%	4,7
Elongation at break	DIN EN ISO 527	%	15,6
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2448
Notched impact strength	DIN EN ISO 179	kJ / m ²	15
Thermal properties			
Melting temperature	ISO 11357-3	°C	>220
Thermal conductivity	DIN 52612-1	W / (m * K)	0,2
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	70
Electrical properties			
Surface resistivity	DIN EN 61340	Ω	> 10 ¹²
Volume resistivity	DIN EN 61340	Ω	> 10 ¹²

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 17/06/2026 • Release: 20/09/2023 • Version: 1.0
 PIM-ID: 709691 • PIM-Code: 89-27-16-7.8.4-12
 Company-IDs: 20070

Page 1 / 1 (Dates in DD/MM/YYYY)

