

Technical Data Sheet

Sustarin[®] H (Delrin[®]) AF 20 - ASTM

POM-H

Typical characteristics

- Good dimensional stability
- Good wear properties
- Good sliding properties

Typical industries

- Conveyor Technology & Automation
- Mechanical Engineering Industry
- Electronics

	Test method	Unit	Guideline value
General properties			
Specific Gravity	ASTM D792	g / cm ³	1.54
Water Absorption 24 hours	ASTM D570	%	0.2
Dissipation Factor	ASTM D150	1MHz	0.009
Water Absorption Saturation	ASTM D570	%	0.8
Mechanical properties			
Hardness	ASTM D785	Shore D	D76
Tensile Strength at yield 73°F	ASTM D638	psi	6630
Tensile Modulus	ASTM D638	psi	540000
Elongation at Break	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	12500
Flexural Modulus	ASTM D790	psi	405000
Compressive Strength	ASTM D695	psi	12600
Rockwell Hardness	ASTM D785		M50
Rockwell Hardness	ASTM D785	R	R110
Thermal properties			
Thermal Conductivity		in/hr/ft ² /F°	2
CTE, linear	ASTM D696	in/in/°F	4.4x10 ⁻⁵
Melting Point	ASTM D3418	°F	350
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	244
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	334

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Continuous Use		°F	185
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150		3.1
Dielectric strength	ASTM D149	V/mil	400
Surface resistivity	ASTM D257	Ω/cm	10 ¹⁶
Compliance properties			
FDA			No
NSF			No
USDA			No

All Information correspond to the current state of our knowledge. The above mentioned values are ranges ascertained by statistical tests on a regular base. They display product information and should be used as guide only to choose from our range of materials. We do not ensure specific properties or suitabilities for particular applications. The material properties rely e.g. on the product dimension, thus the actual value of a particular product may differ from indicated values. Additional specific properties and values can be provided on request. Our material selection for a specific application is based on information by the customer. Despite given recommendation for applications by Röchling Industrial Xanten GmbH, the enduser is still liable to ensure that no third party is affected legally. Furthermore please refer to our general terms and conditions (AGB) <https://www.roechling-industrial.com/gtc>

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/06/2026 • Release: 16/08/2024 • Version: 1.0
 PIM-ID: 717992 • PIM-Code: 30-16-153.126.223-11.5.8-12
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

