

## Technical Data Sheet

# Trafoboard® HD-PH

Pressboard

### Typical characteristics

- Cartón prensado encolado con resina fenólica según IEC 60763-3-1 tipo LB 3.1A.2
- Fabricado con cartón prensado de transformador prensado en caliente, 100% celulosa al sulfato sin blanquear, según IEC 60641-3-1 tipo 3.1
- Aislamiento eléctrico
- Buenas propiedades mecánicas

### Typical industries

- Transformadores
- Sector eléctrico
- Componentes de aislamiento eléctrico
- Transformadores de aceite

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1.15 - 1.35
<b>Mechanical properties</b>			
Flexural strength $\perp$ (MD)	IEC 60763-2	MPa	120
Flexural strength $\perp$ (CMD)	IEC 60763-2	MPa	110
Flexural modulus $\perp$ (MD)	IEC 60763-2	MPa	13000
Flexural modulus $\perp$ (CMD)	IEC 60763-2	MPa	10500
Compressibility (C)	IEC 60763-2	%	2.6
Compressibility (Crev)	IEC 60763-2	%	93
<b>Thermal properties</b>			
Insulation class	IEC 60085	/	A
<b>Physical properties</b>			
Shrinkage (MD)	IEC 60763-2	%	0.20
Shrinkage (CMD)	IEC 60763-2	%	0.30
Shrinkage (Thickness)	IEC 60763-2	%	1.50
Moisture content	IEC 60763-2	%	< 5

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Oil absorption	IEC 60763-2	%	10
pH of aqueous extract	IEC 60763-2	pH	7.1
<b>Dielectrical properties</b>			
Field strength at the onset of PD II	HS-OS <sup>1)</sup>	kV / mm	10
Conductivity of aqueous extract	IEC 60763-2	mS/m	7.1
Electric strength in oil at 90° C II	IEC 60243-1	kV / mm	> 9

MD = Machine Direction

CMD = Cross-Machine Direction

<sup>1)</sup> = contact us for further information

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: [www.roechling-industrial.com/gtc](http://www.roechling-industrial.com/gtc)

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Release: 10/01/2024 • Version: 3.0

PIM-ID: 710093 • PIM-Code: 90-19-8.9.13.17-5.11.7.6-6

Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

