

## Technical Data Sheet

# Trovidur<sup>®</sup> EA white

PVC-U

### Typical characteristics

- Good glueability
- Fire class B1 according to DIN 4102 up to 3 mm thickness
- UV-resistant
- Weatherability
- Flame retardant
- Self-Extinguishing after removal of the flame

### Typical industries

- Building industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,45
Water absorption	DIN EN ISO 62	%	≤0,20
Flammability (Thickness 0,9 mm ... 3 mm)	DIN 4102		B1
Flammability (Thickness 0,9 mm ... 3 mm)	NF P 92-501		M1
Flammability (Thickness 1,2 mm)	BS 476 Part 7		Class 1
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	55
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	4
Shore hardness	DIN EN ISO 868	scale D	83
Ball indentation hardness	DIN EN ISO 2039-1	MPa	110
<b>Thermal properties</b>			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	76
Service Temperature		°C	-15 ... +60
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
<b>Electrical properties</b>			

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>15</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	>10 <sup>13</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 30/05/2026 • Release: 16/11/2023 • Version: 3.0  
 PIM-ID: 591093 • PIM-Code: 1095-24-11.15.15.9.16.11-10-5  
 Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

