

## Technický datový list

Durostone<sup>®</sup> UPM S2 bílá

GFK-UP

## Vlastnosti produktu

- Special vinyl ester (VE) resin matrix reinforced with a combination of an e-glass roving mat and fabric
- SMC high-pressure laminate
- High mechanical strength
- High dielectric strength

## Typické oblasti použití

- Elektrotechnický průmysl
- Generátory a motory
- Vysokonapěťový přenos stejnosměrného proudu
- Stavba strojů a zařízení
- Větrná energie
- Balistika

	Testovací metoda	Jednotka	Orientační hodnota
<b>Mechanické vlastnosti</b>			
Hustota	ISO 1183	g / cm <sup>3</sup>	1,95
Pevnost v ohybu <sup>1)</sup> ⊥	ISO 178	MPa	350
Pevnost v ohybu <sup>1)</sup> ⊥ +130°C	ISO 178	MPa	175
Modul pružnosti v ohybu <sup>1)</sup> ⊥	ISO 178	MPa	18000
Modul pružnosti v ohybu <sup>1)</sup> ⊥ +130 °C	ISO 178	MPa	12000
Pevnost v tlaku ⊥	ISO 604	MPa	480
Pevnost v tahu II	ISO 527	MPa	220
Rázová houževnatost II (Charpy)	ISO 179	kJ / m <sup>2</sup>	200
<b>Tepelné vlastnosti</b>			
Hořlavost	UL 94	/	V0 / 5mm
Hustota dýmu & toxicita, třída	NF F 16-101	/	F0
Požární zkouška, třída	NF P 92-501	/	M2
Teplotní index	IEC 60216	T.I.	155
Izolační třída	IEC 60085	/	F
<b>Fyzikální vlastnosti</b>			
Absorpce vody (4 mm tloušťka)	ISO 62	%	< 0,5
<b>Dielektrické vlastnosti</b>			
Elektrická pevnost 90 °C v olejové lázni ⊥	IEC 60243	kV / mm	12

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Vydáno: 20/09/2023 • Verze: 2.0  
 PIM-ID: 710094 • PIM-kód: 1110-45-12.10.23.19-11.4.4.5.10.8-18  
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Testovací metoda	Jednotka	Orientační hodnota
Elektrická pevnost 90 °C v olejové lázni II	IEC 60243	kV/25mm	75
Relativní permitivita (50 Hz)	IEC 60250	$\epsilon_r$	4
Dielektrický ztrátový činitel (50 Hz)	IEC 60250	$\tan \delta$	0,01
Měrný povrchový odpor	IEC 60093	$\Omega$	$10^{10}$
Srovnávací sledovací index	IEC 60112	CTI	600

⊥ = perpendicular to the lamination II = parallel to the lamination

1) Sample size 80 x 10 x 4 mm, support distance 64 mm, tension zone unmachined

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: [www.roechling-industrial.com/gtc](http://www.roechling-industrial.com/gtc)

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Vydáno: 20/09/2023 • Verze: 2.0  
 PIM-ID: 710094 • PIM-kód: 1110-45-12.10.23.19-11.4.4.5.10.8-18  
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

