

## Technický datový list

## Sustatron® PPS GF 40 černý

PPS

## Vlastnosti produktu

- Low creep tendency
- Flame retardant
- Self-extinguishing
- High continuous service temperature
- High stiffness
- Good dimensional stability

## Typické oblasti použití

- Dopravní technika a automatizace
- Stavba strojů a zařízení

	Testovací metoda	Jednotka	Orientační hodnota
<b>Obecné vlastnosti</b>			
Hustota	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,65
Absorpce vody	DIN EN ISO 62	%	0,0
Hořlavost (tloušťka 3 mm / 6 mm)	UL 94		V0 / V0
<b>Mechanické vlastnosti</b>			
Mez kluzu	DIN EN ISO 527	MPa	90
Prodloužení při přetržení	DIN EN ISO 527	%	2
Modul pružnosti v tahu	DIN EN ISO 527	MPa	6500
Tvrdost Shore	DIN EN ISO 868	scale D	92
<b>Tepelné vlastnosti</b>			
Teplota tání	ISO 11357-3	°C	285
Koeficient lineární teplotní roztažnosti	DIN 53752	10 <sup>-6</sup> / K	30
Provozní teplota dlouhodobá	Průměr	°C	0 ... 220
Provozní teplota krátkodobá (max.)	Průměr	°C	250
Teplota tepelné deformace	DIN EN ISO 75, Verf. A, HDT	°C	260

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 16/06/2026 • Vydáno: 20/09/2023

PIM-ID: 591296 • PIM-kód: 1115-5-12.16.12.11.132.153-11.5-4

Company-IDs: 29033

Page 1 / 2 (Dates in DD/MM/YYYY)



properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 16/06/2026 • Vydáno: 20/09/2023  
PIM-ID: 591296 • PIM-kód: 1115-5-12.16.12.11.132.153-11.5-4  
Company-IDs: 29033

Page 2 / 2 (Dates in DD/MM/YYYY)

