

## Technický datový list

Fibracon<sup>®</sup> PTFE upravený

PTFE

## Vlastnosti produktu

- Reduced deformation under load
- Reduced porosity
- Good wear resistance

## Typické oblasti použití

- Výroba nádrží a zařízení pro chemický průmysl
- Výroba vozidel
- Elektronika
- Ropa a plyn
- Stavba strojů a zařízení
- Zdravotní péče
- Potravinářský průmysl
- Větrná energie

	Testovací metoda	Jednotka	Orientační hodnota
<b>Obecné vlastnosti</b>			
Hustota	ISO 12086	g / cm <sup>3</sup>	2.16
<b>Mechanické vlastnosti</b>			
Tvrdost	DIN EN ISO 868	Shore D	59
Pevnost v tahu (23°C)	ISO 527-3	MPa	36
Prodloužení při přetržení	ISO 527-3	%	500
<b>Tepelné vlastnosti</b>			
Provozní teplota		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Vydáno: 20/09/2023  
PIM-ID: 709599 • PIM-kód: 52-40-14.16.143-9.7.8.5.5.27.5.10-1  
Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

