

Technical Data Sheet

Durostone[®] AGZ-S (160)

GFK-AG

Typical industries

- Tecnologia ferroviaria e dei veicoli ferroviari
- Industria elettrica
- Isolanti elettrici

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,9 - 2,1
Mechanical properties			
Flexural strength, lengthwise	ISO 178	MPa	> 170
Flexural modulus, lengthwise	ISO 178	MPa	> 17.000
Tensile strength, lengthwise	ISO 527	MPa	> 170
Tensile modulus, lengthwise	ISO 527	MPa	> 17.000
Compressive strength, perpendicular	ISO 14126	MPa	> 50
Thermal properties			
Temperature index	IEC 60216	T.I.	F (155 °C)
Glass transition temperature	DMA	°C	> 120
Flame resistance properties			
Flammability	EN45545 Version 2020		HL3 R22/R23
Dielectrical properties			
Comparative tracking index	IEC 60112	CTI	600

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 30/04/2026 • Release: 05/03/2024 • Version: 2.0

PIM-ID: 724562 • PIM-Code: 30-104-11.11.7

Company-IDs: 20000-1

Page 1 / 1 (Dates in DD/MM/YYYY)

