

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 15% Graphite

PTFE

### Typical characteristics

- Improved thermal and electrical conductivity
- Reduced deformation under load

### Typical industries

- 화학 가공 산업
- 차량 제조
- 전자 제품
- Oil and Gas
- 기계 공학 산업
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D1457	g / cm <sup>3</sup>	2.05 - 2.25
<b>Mechanical properties</b>			
Hardness	ASTM D1706	Shore D	55 - 59
Tensile Strength (23°C)	ASTM D1457	N/mm <sup>2</sup>	>13
Elongation at Break	ASTM D1457*	%	>180
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

