

Technisches Datenblatt

Fibracon[®] PTFE + 8% (soft) Carbon+ 2% Graphite

PTFE

Typische Eigenschaften

- Weicher Kohlenstoff bietet im Vergleich zu anderen kohlenstoffgefüllten PTFE-Produkten einen geringeren Werkzeugverschleiß
- Verbesserte thermische und elektrische Leitfähigkeit
- Reduzierte Verformung unter Last

Typische Industrien

- Chemischer Anlagenbau
- Fahrzeugbau
- Elektronik
- Öl und Gas
- Maschinen- und Anlagenbau
- Healthcare
- Lebensmittelindustrie
- Windkraft

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
Dichte	ASTM D4894	g / cm ³	2.14
Mechanische Eigenschaften			
Härte	Needle	Shore D	60 - 64
Zugfestigkeit (23°C)	ASTM D4894	MPa	24
Reißdehnung	ASTM D4894	%	300
Thermische Eigenschaften			
Gebrauchstemperaturbereich		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2026 • Release: 20/09/2023
 PIM-ID: 709627 • PIM-Code: 40-40-10.16.14-9.7.8.5.5.27.5.10-1
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

