

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + Anti-Static Filler

PTFE

### Typical characteristics

- La adición de carbono confiere propiedades antiestáticas al material.
- Hay grados disponibles donde la materia prima ha sido aprobada según los estándares de la FDA.

### Typical industries

- Construcción de contenedores químico
- Construcción de vehículos
- Electrónica
- Petróleo y gas
- Construcción de máquinas e instalaciones
- Healthcare
- Industria alimentaria
- Energía eólica

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D4894	g / cm <sup>3</sup>	2.15
<b>Mechanical properties</b>			
Hardness	Needle	Shore D	56
Tensile Strength (23°C)	ASTM D4894	MPa	>20
Elongation at Break	ASTM D4894	%	250
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

