

Technical Data Sheet

Fibracon[®] PTFE virgin

PTFE

Typical characteristics

- Wide operating temperature - 200°C to +260°C
- Low coefficient of friction
- Chemical resistant

Typical industries

- Construction de réservoirs et d'installations chimiques
- Construction de véhicules
- Industrie électronique
- Pétrole et gaz
- Construction de machines et d'installations
- Healthcare
- Industrie agroalimentaire
- Sport et loisirs
- L'énergie éolienne
- Semiconductor Front-End Wet Bench
- Semiconductor Front-End applications

	Test method	Unit	Guideline value
General properties			
Densité	ASTM D4894	g / cm ³	2.17
Mechanical properties			
Hardness	Needle	Shore D	54 - 60
Tensile Strength (23°C)	ASTM D4894	N/mm ²	25
Elongation at Break	ASTM D4894	%	250
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

