

Technical Data Sheet

Glastherm[®] HT 250 HQ - ASTM

GFK-UP

Typical characteristics

- Low thermal conductivity
- Heat resistant
- Fibre-reinforced composite material developed for applications in field of thermal insulation (max. continuous operating temperature 250°C)
- Reduces Heat Loss

Typical industries

- Chemical Processing Industry
- Mechanical Engineering Industry
- Pipelines
- Oil and Gas

	Test method	Unit	Guideline value
General properties			
Standard Color			Light Green
Maximum Service Temp.		°C	400
Continuous Use Temp.		°C	250
Mechanical properties			
Flexural Strength	ASTM D 790	psi	87,000
Compressive Strength @RT	ASTM D 695	psi	87,000
Compressive Strength @356°F / 180°C	ASTM D 695	psi	72,500
Thermal properties			
Coefficient of Thermal Expansion Across Thickness	ASTM D 696	(in./in.°C) x 10-5	11.6
Coefficient of Thermal Expansion Across Surface	ASTM D 696	(in./in.°C) x 10-5	1.3
Thermal Conductivity	ASTM C 177	BTUIn/HrFt ² °F	1.54
Physical properties			
Density	ASTM D 792	lbs/ft ³	125
Water Absorption	ASTM D 570	% by wt.	0.10
Thickness Tolerance		inches	+/-0.004
Dielectrical properties			
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	300

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 29/04/2026 • Release: 12/11/2024 • Version: 4.0
 PIM-ID: 715301 • PIM-Code: 64-26-12.11.11.10-9.5.5-6
 Company-IDs: 23050

Page 1 / 2 (Dates in DD/MM/YYYY)



such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 29/04/2026 • Release: 12/11/2024 • Version: 4.0
PIM-ID: 715301 • PIM-Code: 64-26-12.11.11.10-9.5.5-6
Company-IDs: 23050

Page 2 / 2 (Dates in DD/MM/YYYY)

