

## Technical Data Sheet

# Glastherm<sup>®</sup> S

### Typical characteristics

- Low thermal conductivity
- Heat resistant
- Reduces Heat Loss
- Fibre-reinforced composite material developed for applications in field of thermal insulation (max. continuous operating temperature 218°C)

### Typical industries

- Chemical Processing Industry
- Mechanical Engineering Industry
- Pipelines
- Oil and Gas

	Test method	Unit	Guideline value
<b>General properties</b>			
Standard Color			Tan
Maximum Service Temp.		°C	218
<b>Mechanical properties</b>			
Flexural Strength	ASTM D 790	psi	18,000
Compressive Strength @75°F / 24°C	ASTM D 695	psi	45,000
Compressive Strength @302°F / 150°C	ASTM D 695	psi	16,000
Compressive Strength @392°F / 200°C	ASTM D 695	psi	11,500
Compressive Strength @550°F / 288°C	ASTM D 695	psi	10,000
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	8
<b>Thermal properties</b>			
Coefficient of Thermal Expansion Across Thickness	ASTM D 696	(in./in.°C) x 10-5	7.02
Coefficient of Thermal Expansion Across Surface	ASTM D 696	(in./in.°C) x 10-5	1.10
Thermal Conductivity	ASTM C 177		1.8
<b>Flame resistance properties</b>			
UL Subject 94	UL 94		HB
<b>Physical properties</b>			
Density	ASTM D 792	lbs/ft <sup>3</sup>	115
Water Absorption	ASTM D 570	% by wt.	0.4
Thickness Tolerance		inches	+/-0.002

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
<b>Dielectrical properties</b>			
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	50

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 29/04/2026 • Release: 20/09/2023 • Version: 1.0  
PIM-ID: 715303 • PIM-Code: 41-20-12.11.10.13-9.5.5.5-6  
Company-IDs: 23050

Page 2 / 2 (Dates in DD/MM/YYYY)

