

## Technical Data Sheet

# Lamigamid<sup>®</sup> 1200

PA 12 G

### Typical characteristics

- High impact strength even at low temperatures
- Good wear resistance
- Hydrolysis resistant
- Chemical resistant

### Typical industries

- 컨베이어 기술 및 자동화
- 기계 공학 산업
- 크레인 및 인양 기술
- Elevators and Escalators

|                               | Test method       | Unit                | Guideline value |
|-------------------------------|-------------------|---------------------|-----------------|
| <b>General properties</b>     |                   |                     |                 |
| Density                       | DIN EN ISO 1183-1 | g / cm <sup>3</sup> | 1,02-1,03       |
| Water absorption              | DIN EN ISO 62     | %                   | 0,7-0,8         |
| <b>Mechanical properties</b>  |                   |                     |                 |
| Yield stress                  | DIN EN ISO 527    | MPa                 | 50-55           |
| Elongation at break           | DIN EN ISO 527    | %                   | 40-55           |
| Tensile modulus of elasticity | DIN EN ISO 527    | MPa                 | 1900-2100       |
| Notched impact strength       | DIN EN ISO 179    | kJ / m <sup>2</sup> | 10-14           |
| <b>Thermal properties</b>     |                   |                     |                 |
| Melting temperature           | ISO 11357-3       | °C                  | 185-195         |

All Information correspond to the current state of our knowledge. The above mentioned values are ranges ascertained by statistical tests on a regular base. They display product information and should be used as guide only to choose from our range of materials. We do not ensure specific properties or suitabilities for particular applications. The material properties rely e.g. on the product dimension, thus the actual value of a particular product may differ from indicated values. Additional specific properties and values can be provided on request. Our material selection for a specific application is based on information by the customer. Despite given recommendation for applications by Roechling Industrial Xanten GmbH, the enduser is still liable to ensure that no third party is affected legally. Furthermore please refer to our general terms and conditions (AGB) <https://www.roechling.com/gtc>

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

