

## Technical Data Sheet

# Lamigamid<sup>®</sup> 314

PA 6 G

### Typical characteristics

- Good machinability
- Good fatigue strength
- Filled with solid lubricant

### Typical industries

- Mechanical Engineering Industry
- Crane and Lifting Technology

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,14-1,16
Water absorption	DIN EN ISO 62	%	6,1-6,4
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	70-85
Elongation at break	DIN EN ISO 527	%	20-70
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3400-4100
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	4,0-10,5
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	220-230

All information correspond to the current state of our knowledge. The above mentioned values are ranges ascertained by statistical tests on a regular base. They display product information and should be used as guide only to choose from our range of materials. We do not ensure specific properties or suitabilities for particular applications. The material properties rely e.g. on the product dimension, thus the actual value of a particular product may differ from indicated values. Additional specific properties and values can be provided on request. Our material selection for a specific application is based on information by the customer. Despite given recommendation for applications by Röchling Industrial Xanten GmbH, the enduser is still liable to ensure that no third party is affected legally. Furthermore please refer to our general terms and conditions (AGB) <https://www.roechling.com/gtc>

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 29/04/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 709658 • PIM-Code: 26-28-70.13.9-5.8-12  
 Company-IDs: 20220

Page 1 / 1 (Dates in DD/MM/YYYY)

