

Technical Data Sheet

LubX[®] C blue extruded

PE-UHMW / PE 1000

Typical characteristics

- Energy-saving
- Especially aligned to POM and Steel
- FDA/21CFR177.1520 compliant
- Noise-reducing
- Coefficient of friction with POM as sliding partner up to 75% less than of PE-UHMW
- Coefficient of friction with steel as sliding partner up to 60% less than of PE-UHMW

Typical industries

- 기계 공학 산업
- 건설업
- 컨베이어 기술 및 자동화
- Food Industry
- Meat, Fish and Poultry Processing
- Bakery and Confectionery
- Beverage Industry


	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,93
Water absorption	DIN EN ISO 62	%	0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	650
Notched impact strength	DIN EN ISO 179	kJ / m ²	no break
Shore hardness	DIN EN ISO 868	scale D	60
Sliding partner POM MOD A (0,25 m/s - 0,25 MPa)	REP - Tribology - Test		0,08
Sliding partner POM MOD B (0,25 m/s - 0,25 MPa)	REP - Tribology - Test		0,11
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 – 135

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Coefficient of linear thermal expansion	DIN 53752	$10^{-6} / \text{K}$	150 - 230 (*)
Service temperature, long term	Average	$^{\circ}\text{C}$	-150 ... 80 (*)
Service temperature, short term (max.)	Average	$^{\circ}\text{C}$	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{14}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (*) literature values



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

