

Technical Data Sheet

LubX[®] CV blue extruded

PE-UHMW / PE 1000

Typical characteristics

- Excelentes propiedades de deslizamiento incluso con cargas más altas
- Excelentes propiedades de funcionamiento en seco
- Cumple con la normativa alimentaria según 10/2011/UE, 1935/2004/CE, FDA
- Buena maquinabilidad
- Cumple con GMP según 2023/2006 CE

Typical industries

- Construcción de máquinas e instalaciones
- Industria del papel
- Sistemas de transporte y automatización
- Industria alimentaria
- Procesamiento de carne, pescado y aves de corral
- Productos de bollería y dulces
- Industria de bebidas

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,94
Water absorption	DIN EN ISO 62	%	0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	>250
Tensile modulus of elasticity	DIN EN ISO 527	MPa	500
Notched impact strength	DIN EN ISO 179	kJ / m ²	no break
Shore hardness	DIN EN ISO 868	scale D	60
Sliding properties: partner POM (0,5 m/s - 0,5 MPa)	REP - Tribology - Test		0,13
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 - 135
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{14}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (*) literature values



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 03/05/2026 • Release: 23/05/2025 • Version: 8.0
 PIM-ID: 718556 • PIM-Code: 934-32-16.18.11.70.15-5.8.11.5.5.6-4
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

