

テクニカルデータシート

MAYWOflamm[®] PS

PS

製品の特徴

- 耐火性

製品の用途例

- エレクトロニクス
- 真空成形

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	1,16
燃焼性	UL 94		V0 (2mm)
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	19
引張破壊伸び	DIN EN ISO 527	%	44
引張弾性率	DIN EN ISO 527	MPa	2033
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m ²	8
熱的物性			
融点	ISO 11357-3	°C	> 150 °C
熱伝導率	DIN 52612-1	W / (m * K)	0,17
線膨張係数	DIN 53752	10 ⁻⁶ / K	90
ビカットB軟化温度	DIN EN ISO 306, Vicat B	°C	87
グローワイヤテスト	DIN EN 60695-2	°C	825 (0,5mm/ 0,8mm)
電氣的物性			
表面固有抵抗	DIN EN 61340	Ω	> 10 ¹²
体積固有抵抗	DIN EN 61340	Ω	> 10 ¹²

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2026 • Release: 20/09/2023 • Version: 4.0

PIM-ID: 709696 • PIM-Code: 73-15-16-8.4-12

Company-IDs: 20070

Page 1 / 1 (Dates in DD/MM/YYYY)

