

## テクニカルデータシート

Maywoblend<sup>®</sup> PS/PE CR

PS

## 製品の特徴

- 柔らかい感触

## 製品の用途例

- 真空成形

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,0
吸水率	DIN EN ISO 62	%	0,1
<b>機械的物性</b>			
引張降伏応力	DIN EN ISO 527	MPa	11
引張破壊呼び歪	DIN EN ISO 527	%	>150
引張弾性率	DIN EN ISO 527	MPa	735
<b>熱的物性</b>			
融点	ISO 11357-3	°C	>170°C
ピカットB軟化温度	DIN EN ISO 306, Vicat B	°C	79,7
<b>電気的物性</b>			
表面固有抵抗	DIN EN 61340	Ω	> 10 <sup>12</sup>
体積固有抵抗	DIN EN 61340	Ω	> 10 <sup>12</sup>

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

