

Technical Data Sheet



Maywogreen PS PCR[®] 1230

PS

Typical characteristics

- RoHS compliant

Typical industries

- Vacuum Forming

Sustainability

- Post-Consumer-Recycling material
- The use of recycled materials conserves valuable resources

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,06
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	13
Elongation at break	DIN EN ISO 527	%	24
Notched impact strength	DIN EN ISO 179	kJ / m ²	7
Thermal properties			
Melting temperature	ISO 11357-3	°C	> 170 °C
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	81
Electrical properties			
Surface resistivity	DIN EN 61340	Ω	> 10 ¹²
Volume resistivity	DIN EN 61340	Ω	> 10 ¹²

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

