

Technical Data Sheet

Polystone[®] G CubX[®] black

PE-HD (PE 100)

Typical characteristics

- Alta rigidez longitudinal y transversal
- Peso ligero, fácil manejo
- Bajo peso
- Buen aislamiento térmico
- Buena maquinabilidad
- Buena soldabilidad
- Resistencia química

Typical industries

- Construcción de contenedores químicos
- Agua potable y tratamiento de aguas residuales
- Tanques de almacenamiento
- Construcción de máquinas e instalaciones
- Acuicultura

	Test method	Unit	Guideline value
Properties for the full cross-ribbed twin-wall sheet			
Thermal conductivity	ISO 8302 Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,16
Density	DIN EN ISO 1183	g / cm ³	0,3
Area weight		kg/m ²	18,6
Weld strength lattice / covering sheets		MPa	≥ 16
Flatness	DIN EN ISO 15860	mm/m	4
Properties for the covering sheets			
Density, RT	DIN EN ISO 1183	g / cm ³	0,96
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	> 50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1000
Notched impact strength	DIN EN ISO 179	kJ / m ²	20
Dielectric constant	IEC 60250		2,5
Surface resistivity	DIN EN 62631-3-2		>10 ¹⁴

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

