

Technical Data Sheet

Polystone[®] M Green - ASTM

PE-UHMW / PE 1000

Typical characteristics

- Low coefficient of friction
- Good wear properties
- Good impact strength

Typical industries

- Mechanical Engineering Industry
- Conveyor Technology & Automation
- Food Industry


	Test method	Unit	Guideline value
General properties			
Specific Gravity	ASTM D792	g / cm ³	0.93
Water Absorption	ASTM D570	%	0.10
Mechanical properties			
Wear resistance	Sand-slurry		100
Hardness	ASTM D2240	Shore D	62 - 66
Tensile Strength at yield 73°F	ASTM D638	psi	3100
Tensile Modulus	ASTM D638	psi	100000
Elongation at Break	ASTM D638	%	>350
Flexural Strength	ASTM D790	psi	3500
Compressive Strength	ASTM D695	psi	3000
Izod Impact, Notched	ASTM D256	ft-lb/in	No Break
Coefficient of Friction, Dynamic			0.10-0.22
Coefficient of Friction, Static			0.15-0.20
Izod Impact Strength	ASTM D4020	kJ / m ²	125
Thermal properties			
CTE, linear	ASTM D696	in/in/°F	1.1x10 ⁻⁴
Melting Point	ASTM D3418	°F	266 - 275
Vicat Softening Point	ISO306	°F	176
Continuous Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	108

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Flammability, UL94		1/8 inch	HB
Electrical properties			
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 20/04/2026 • Release: 07/08/2025 • Version: 6.0
 PIM-ID: 774085 • PIM-Code: 46-19-12.126.162-5.11.5-5
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

