

テクニカルデータシート

Polystone[®] P (Copolymer) blue

PP-C

製品の特徴

- 高剛性
- 良好な溶接性
- 耐腐食性

Sustainability

- LCA available (ISO 14040/44)

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	>0,91
吸水率	DIN EN ISO 62	%	0,1
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	>23
引張破壊呼び歪	DIN EN ISO 527	%	>50
引張弾性率	DIN EN ISO 527	MPa	>1100
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m ²	>30
シヨア硬度	DIN EN ISO 868	scale D	>65
熱的物性			
融点	ISO 11357-3	°C	162 ... 165
熱伝導率	DIN 52612-1	W / (m * K)	0,20
熱容量	DIN 52612	kJ / (kg * K)	1,70
線膨張係数	DIN 53752	10 ⁻⁶ / K	120 ... 190
使用温度 (長期)	平均値	°C	-30 ... 100
使用温度 (短期、最大)	平均値	°C	150
ビカットB軟化温度	DIN EN ISO 306, Vicat B	°C	85
電気的物性			
誘電率	IEC 60250		2,5
誘電正接 (10 ⁶ Hz)	IEC 60250		0,00019
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 02/05/2026 • Release: 19/01/2026 • Version: 3.0

PIM-ID: 718602 • PIM-Code: 1060-8-11.16.21-3-5

Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
表面固有抵抗	DIN EN 62631-3-2	Ω	$>10^{14}$
比較トラッキング指数	IEC 60112		600
絶縁破壊電圧	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 02/05/2026 • Release: 19/01/2026 • Version: 3.0
 PIM-ID: 718602 • PIM-Code: 1060-8-11.16.21-3-5
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

