

## Technical Data Sheet

# Polystone<sup>®</sup> P CubX<sup>®</sup> (Copolymer) PG + UV-stabilized white

PP-C

### Typical characteristics

- Alta rigidez longitudinal y transversal
- Peso ligero, fácil manejo
- Bajo peso
- Buen aislamiento térmico
- Buena maquinabilidad
- Buena soldabilidad
- Resistencia química
- resistente a los rayos UV

### Typical industries

- Deporte y ocio
- Agua potable y tratamiento de aguas residuales
- Tanques de almacenamiento
- Láminas de plástico para piscinas

	Test method	Unit	Guideline value
<b>Properties for the full cross-ribbed twin-wall sheet</b>			
Thermal conductivity	ISO 8302   Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,14
Density	DIN EN ISO 1183	g / cm <sup>3</sup>	0,3
Area weight		kg/m <sup>2</sup>	17,1
Weld strength lattice / covering sheets		MPa	≥ 20
Flatness	DIN EN ISO 15860	mm/m	≤ 3
Water absorption	DIN EN ISO 62	%	0,1
<b>Properties for the covering sheets</b>			
Density, RT	DIN EN ISO 1183	g / cm <sup>3</sup>	0,92
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	> 50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1200
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	> 30

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)





[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 02/05/2026 • Release: 05/05/2025 • Version: 2.0  
PIM-ID: 710120 • PIM-Code: 1128-5-11.20.14.11.70.16.33.15-3.6.7.8-5  
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

