

Technický datový list

Polystone[®] P CubX[®] (Copolymer) PG + UV-stabilizovaný bílá

PP-C

Vlastnosti produktu

- High longitudinal and transversal stiffness
- Good handling
- Low weight
- Good thermal insulation
- Good machinability
- Good weldability
- Chemical resistant
- UV-resistant

Typické oblasti použití

- Sport a volný čas
- Technologie pitné a odpadní vody
- Skladovací nádrže
- Plastové desky pro bazény

	Testovací metoda	Jednotka	Orientační hodnota
Bezpečnostní list			
Tepelná vodivost	ISO 8302 Testováno s: GHP 500-1, proces s jednou deskou	W / (m * K)	Lambda 0,14
Hustota	DIN EN ISO 1183	g / cm ³	0,3
Plošná hmotnost		kg/m ²	17,1
Svařovací mřížka / svrchní desky		MPa	≥ 20
Rovinnost	DIN EN ISO 15860	mm/m	≤ 3
Absorpce vody	DIN EN ISO 62	%	0,1
Vlastnosti svrchních desek			
Hustota, RT	DIN EN ISO 1183	g / cm ³	0,92
Mez kluzu	DIN EN ISO 527	MPa	24
Prodloužení při přetržení	DIN EN ISO 527	%	> 50
Modul pružnosti v tahu	DIN EN ISO 527	MPa	1200
Vrubová houževnatost	DIN EN ISO 179	kJ / m ²	> 30

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

