

## Technical Data Sheet

# Polystone<sup>®</sup> P copolymer EHS grey - ASTM

PP

### Typical characteristics

- High rigidity
- Good weldability
- Corrosion resistant

### Typical industries

- Aquafarming
- Clean-Room Technology
- Drinking & Waste Water Technology
- Chemical Processing Industry
- Chemical storage tanks
- Galvanic plants
- Steel-pickling plants
- Ventilation plants
- Exhaust-air cleaning plants

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	0.91
Water Absorption	ASTM D570	%	0.10
Carbon Black Content	ISO6964	%	n/a
<b>Mechanical properties</b>			
Tensile Strength at Yield	ASTM D638	psi	3500
Hardness	ASTM D2240	Shore D	69
Tensile Elongation	ASTM D638	%	>300
Flexural Modulus	ASTM D790	psi	155000
Compressive Strength	ASTM D695	psi	4000
Izod Impact, Notched	ASTM D256	ft-lb/in	8
Coefficient of Friction, Dynamic			0.25-0.28
<b>Thermal properties</b>			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	6
Melting Point		°F	323
Maximum Service Temperature, Air		°F	230
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	210

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 29/04/2026 • Release: 20/09/2023

PIM-ID: 717984 • PIM-Code: 37-21-11.16.21-5.7.6.9.7.4.6.4.4-2


Company-IDs: 23070

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	217
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	2.5
Dielectric strength	ASTM D149	kV / mm	45
Surface resistivity	ASTM D257	Ω/cm	>10 <sup>14</sup>
<b>Compliance properties</b>			
FDA			Yes
NSF			No
USDA			Yes
ASTM Approval			D-4101

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 29/04/2026 • Release: 20/09/2023  
 PIM-ID: 717984 • PIM-Code: 37-21-11.16.21-5.7.6.9.7.4.6.4.4-2  
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

