

## Technical Data Sheet

# Polystone<sup>®</sup> P copolymer grey - ASTM

PP

### Typical characteristics

- Chemical resistant
- Good weldability
- Good impact strength

### Typical industries

- Aquafarming
- Clean-Room Technology
- Drinking & Waste Water Technology
- Chemical Processing Industry
- Chemical storage tanks
- Galvanic plants
- Steel-pickling plants
- Ventilation plants
- Exhaust-air cleaning plants

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	0,91
Water Absorption	ASTM D570	%	≤0.1
<b>Mechanical properties</b>			
Hardness	ASTM D785	Shore D	69
Tensile Strength at yield 73°F	ASTM D638	psi	3500
Elongation at Break	ASTM D638	%	≥300
Flexural Strength	ASTM D790	psi	155,000
Compressive Strength	ASTM D695	psi	4000
Izod Impact, Notched	ASTM D256	ft-lb/in	8
Coefficient of Friction, Dynamic			0,25-0,28
<b>Thermal properties</b>			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	6
Melting Point	ASTM D1525	°F	323
Maximum Service Temperature, Air		°F	180
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	210
Flammability, UL94		1/8 inch	HB

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	2,5
Dielectric strength	ASTM D149	V/mil	45
Surface resistivity	ASTM D257	Ω/cm	≥10 <sup>14</sup>
<b>Compliance properties</b>			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 29/04/2026 • Release: 20/09/2023  
 PIM-ID: 717968 • PIM-Code: 40-21-33.16.162-5.7.6.9.7.4.6.4.4-2  
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

