

Technical Data Sheet

Polystone® P flex

PP

Typical characteristics

- Resistencia química
- Buena dureza
- Buena resistencia al desgaste
- Soldable con Polystone® P
- Alta elasticidad

Typical industries

- Construcción de contenedores químico
- Plantas de galvanizado
- Sistemas de ventilación
- Tanques de almacenamiento

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,88
Water absorption	DIN EN ISO 62	%	0,05
Melt Flow Rate (MFR 190/5)	DIN EN ISO 1133	g / 10 min	0,6
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	>800
Tensile modulus of elasticity	DIN EN ISO 527	MPa	200
Shore hardness	DIN EN ISO 868	scale D	35
Thermal properties			
Melting temperature	ISO 11357-3	°C	144

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

