

### Technical Data Sheet

## Polystone® P flex

PP

#### Typical characteristics

- Chemical resistant
- Good toughness
- Good wear resistance
- Weldable with Polystone® P
- High Elasticity

#### Typical industries

- Construction de réservoirs et d'installations chimiques
- Stations de galvanisation
- Systèmes de ventilation
- Réservoirs de stockage

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,88
Water absorption	DIN EN ISO 62	%	0,05
Melt Flow Rate (MFR 190/5)	DIN EN ISO 1133	g / 10 min	0,6
<b>Mechanical properties</b>			
Elongation at break	DIN EN ISO 527	%	>800
Tensile modulus of elasticity	DIN EN ISO 527	MPa	200
Shore hardness	DIN EN ISO 868	scale D	35
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	144

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

