

## テクニカルデータシート

Polystone<sup>®</sup> Safe-Tec C black

PE-HD (PE 100)

## 製品の特徴

- 表面にTPE素材使用
- 良好な溶接性
- 耐薬品性

## 製品の用途例

- 化学産業

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,95
吸水率	DIN EN ISO 62	%	0,01
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
燃焼性 (厚み 3 - 10 mm)	DIN 4102		B2
<b>機械的物性</b>			
引張降伏応力	DIN EN ISO 527	MPa	>22
引張破壊伸び	DIN EN ISO 527	%	>50
引張弾性率	DIN EN ISO 527	MPa	>1000
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m <sup>2</sup>	>10
ショア硬度	DIN EN ISO 868	scale D	>38
<b>熱的物性</b>			
融点	ISO 11357-3	°C	130 ... 135
熱伝導率	DIN 52612-1	W / (m * K)	0,40
熱容量	DIN 52612	kJ / (kg * K)	1,90
線膨張係数	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
使用温度 (長期)	平均値	°C	-50 ... 80
使用温度 (短期、最大)	平均値	°C	100
ピカットB軟化温度	DIN EN ISO 306, Vicat B	°C	67
<b>電氣的物性</b>			
誘電率	IEC 60250		2,4
誘電正接 (10 <sup>6</sup> Hz)	IEC 60250		0,0004

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 28/04/2026 • Release: 11/11/2024 • Version: 1.0

PIM-ID: 591187 • PIM-Code: 1117-29-9.16.33-9-10.5

Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
体積固有抵抗	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{14}$
表面固有抵抗	DIN EN 62631-3-2	$\Omega$	$>10^{14}$
比較トラッキング指数	IEC 60112		600
絶縁破壊電圧	IEC 60243	kV / mm	$>40$

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

One-sided coating can lead to unpreventable material distortion under certain circumstances.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 28/04/2026 • Release: 11/11/2024 • Version: 1.0  
 PIM-ID: 591187 • PIM-Code: 1117-29-9.16.33-9-10.5  
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

