

Technical Data Sheet

SustaPEEK CM CT200

PEEK

Typical characteristics

- High cold impact strength
- High heat deflection temperature
- Good sliding properties
- Chemical resistant
- NORSOK M710 compliant

Typical industries

- Oil and Gas
- Semiconductor Industry
- Aerospace
- Chemical Processing Industry

| | Test method | Unit | Guideline value |
|--|-------------------|---------------------|-----------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | 1,43 |
| Mechanical properties | | | |
| Elongation at break | DIN EN ISO 527 | % | 4 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | 3200 |
| Tensile strength | DIN EN ISO 527 | MPa | 70 |
| Notched impact strength | DIN EN ISO 179 | kJ / m ² | 3,5 |
| Shore hardness | DIN EN ISO 868 | scale D | 86 |
| Elastic modulus of compression | DIN EN ISO 604 | MPa | 3250 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 330 |
| Service temperature, long term | Average | °C | -200...250 |
| Service temperature, short term (max.) | Average | °C | 300 |

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

