

テクニカルデータシート

SustaPEI GF 30 natural

PEI

製品の特徴

- 高熱たわみ温度
- 耐火性
- 煙の発生が極めて少ない
- 高い剛性
- 高い引張強度
- 高い硬度
- 熱下での高い寸法安定性

製品の用途例

- エレクトロニクス
- ヘルスケア
- 航空宇宙

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	1,51
吸水率	DIN EN ISO 62	%	0,4
燃焼性 (厚み 3 mm / 6 mm)	UL 94		V0 / V0
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	120
引張破壊呼び歪	DIN EN ISO 527	%	4
引張弾性率	DIN EN ISO 527	MPa	5000
シヨア硬度	DIN EN ISO 868	scale D	92
熱的物性			
融点	ISO 11357-3	°C	-
ガラス転移温度	ISO 11357-3	°C	217
使用温度 (長期)	平均値	°C	-30 ... 170
使用温度 (短期、最大)	平均値	°C	210
荷重たわみ温度	DIN EN ISO 75, Verf. A, HDT	°C	210
電氣的物性			
誘電率	IEC 60250		3,3
誘電正接 (50 Hz)	IEC 60250		0,0016
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	10 ¹⁵

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 29/04/2026 • Release: 20/09/2023

PIM-ID: 591394 • PIM-Code: 1114-38-11.16.15.132.12.11.11-8.27.8-6

Company-IDs: 29033

Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
表面固有抵抗	DIN EN 62631-3-2	Ω	10 ¹⁵
比較トラッキング指数	IEC 60112		150
絶縁破壊電圧	IEC 60243	kV / mm	35

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5,000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 29/04/2026 • Release: 20/09/2023
 PIM-ID: 591394 • PIM-Code: 1114-38-11.16.15.132.12.11.11-8.27.8-6
 Company-IDs: 29033

Page 2 / 2 (Dates in DD/MM/YYYY)

