

Technical Data Sheet

Sustamid® 12 GF 30 natural

PA 12

Typical characteristics

- High heat deflection temperature
- Good noise absorption properties
- Vibration damping
- High abrasion resistance
- High stiffness
- Good compressive strength
- High mechanical strength

Typical industries

- Ingegneria meccanica e impiantistica

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,25
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB / HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	60
Elongation at break	DIN EN ISO 527	%	10
Tensile modulus of elasticity	DIN EN ISO 527	MPa	4000
Notched impact strength	DIN EN ISO 179	kJ / m ²	5
Shore hardness	DIN EN ISO 868	scale D	86
Thermal properties			
Melting temperature	ISO 11357-3	°C	180
Thermal conductivity	DIN 52612-1	W / (m * K)	0,28
Thermal capacity	DIN 52612	kJ / (kg * K)	1,50
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	60
Service temperature, long term	Average	°C	-30 ... 110
Service temperature, short term (max.)	Average	°C	180
Heat deflection temperature	DIN EN ISO 75, Verf. A, HDT	°C	140

The following applies to Polyamides: Under the influence of moisture absorption, the mechanical properties change. The material becomes tougher and more resistant to impact, the modulus of elasticity declines. Depending on the environmental atmosphere, the temperature and the period of moisture absorption, only the surface layer is

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2026 • Release: 20/09/2023 • Version: 1.0
 PIM-ID: 591044 • PIM-Code: 1129-30-11.10.10.63.132.19.23-5-4
 Company-IDs: 29033

Page 1 / 2 (Dates in DD/MM/YYYY)



affected by alterations of property to a certain depth. On thick-walled parts, the center area remains unaffected. The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to an minimum degree of impact stress. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2026 • Release: 20/09/2023 • Version: 1.0
PIM-ID: 591044 • PIM-Code: 1129-30-11.10.10.63.132.19.23-5-4
Company-IDs: 29033

Page 2 / 2 (Dates in DD/MM/YYYY)

