

## Technical Data Sheet

# Sustamid<sup>®</sup> 6G OL - ASTM

PA 6 G

### Typical characteristics

- Self-lubricating
- Good "stick-slip" properties
- High absorption of moisture of up to 3 % in standard atmosphere
- Good sliding properties

### Typical industries

- Mechanical Engineering Industry
- Conveyor Technology & Automation

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.15
Water Absorption	ASTM D570	%	5.0
Water Absorption 24 hours	ASTM D570	%	1.0
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	74
Tensile Strength at yield 73°F	ASTM D638	psi	11000
Tensile Modulus	ASTM D638	psi	370000
Elongation at Break	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	14000
Flexural Modulus	ASTM D790	psi	380000
Compressive Strength	ASTM D695	psi	13500
Rockwell Hardness	ASTM D785		85
Rockwell Hardness	ASTM D785	R	115
Shear Strength	ASTM D732	psi	8000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.12
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.7
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	5.0
Melting Point		°F	430

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Continuous Service Temperature, Air		°F	210
Flammability, UL94		1/8 inch	HB
Deflection Temperature at 264psi	ASTM D648	°F	200
Deflection Temperature at 66psi	ASTM D648	°F	380
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	3.7
Dielectric strength	ASTM D149	V/mil	500
Surface resistivity	ASTM D257	Ω/cm	>10 <sup>13</sup>
<b>Compliance properties</b>			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 29/04/2026 • Release: 26/12/2024 • Version: 2.0  
 PIM-ID: 717919 • PIM-Code: 38-19-10.14.14.223-5.11-2  
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

