

テクニカルデータシート

Sustatron[®] PPS natural

PPS

製品の特徴

- 高い連続使用温度
- 高い硬度
- 高剛性
- 耐火性
- 自己消化性
- 良好な機械加工性
- 電気絶縁性
- 耐薬品性

製品の用途例

- コンベヤー
- 機械工学
- 半導体
- 半導体-フロントエンド用途
- 半導体-CMP
- 半導体-バックエンド用途
- 半導体-CMP
- 半導体-バックエンド用途

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	1,35
吸水率	DIN EN ISO 62	%	0,0
燃焼性 (厚み 3 mm / 6 mm)	UL 94		V0 / V0
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	90
引張破壊呼び歪	DIN EN ISO 527	%	3
引張弾性率	DIN EN ISO 527	MPa	4150
シヨア硬度	DIN EN ISO 868	scale D	88
熱的物性			
融点	ISO 11357-3	°C	285
使用温度 (長期)	平均値	°C	-20 ... 220
使用温度 (短期、最大)	平均値	°C	260
荷重たわみ温度	DIN EN ISO 75, Verf. A, HDT	°C	110
電氣的物性			
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	10 ¹³
表面固有抵抗	DIN EN 62631-3-2	Ω	10 ¹⁵

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 28/04/2026 • Release: 06/06/2024 • Version: 2.0
PIM-ID: 591260 • PIM-Code: 1158-30-11.11.11.16.12.70.13.33-11.5.11.10.7.11.5.7-6
Company-IDs: 29033

Page 2 / 2 (Dates in DD/MM/YYYY)

