

Technical Data Sheet

Astrawood® COOL woodgrain decor

PVC-U

Typical characteristics

- Laminated on one side with different, high-quality decorative foils
- High impact resistance
- Good weather resistance

Typical industries

- 건설업

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,41
Water absorption	DIN EN ISO 62	%	0,2
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	45
Elongation at break	DIN EN ISO 527	%	20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2500
Notched impact strength	DIN EN ISO 179	kJ / m ²	8
Shore hardness	DIN EN ISO 868	scale D	77
Ball Hardness	ISO 2039	MPa	100
Compressive strength	DIN EN ISO 604	MPa	65
Bending strength	DIN EN ISO 178	MPa	60
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	76
Service Temperature		°C	-10 ... +60
Heat deflection temperature	DIN EN ISO 75	°C	70
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Electrical properties			
Dielectric constant	IEC 60250		3,20
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02

ri-inquiry@roechling.com • www.roechling.com/industrial/materials


Print: 15/12/2025 • Release: 17/12/2024 • Version: 4.0
PIM-Version: 1021 • PIM-ID: 591161 • PIM-Code: 1021-16-13.18.61-10-2
Company-IDs: 20000-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{13}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. Information on the REACH regulation can be found in our Product Handling Information Sheets, in our REACH information letter as well as in the SCIP database.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 15/12/2025 • Release: 17/12/2024 • Version: 4.0
PIM-Version: 1021 • PIM-ID: 591161 • PIM-Code: 1021-16-13.18.61-10-2
Company-IDs: 20000-2

