

## Technical Data Sheet

# DuroProtect<sup>®</sup> 1000

### Typical characteristics

- UL® Recognized
- Lightweight composite ballistic-resistant sheet, designed to provide protection from bullets and shrapnel
- Custom Sizes Available

### Typical industries

- Ballistics
- Building industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Part Number			1717
Standard Color			Off-White
<b>Mechanical properties</b>			
Compressive Strength	ASTM D 695	psi	70,000
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	52
Tensile Strength, lengthwise	ASTM D 638	psi	45,000
Tensile Strength, crosswise	ASTM D 638	psi	40,000
Flexural Strength, lengthwise	ASTM D 790	psi	16,800
<b>Thermal properties</b>			
UL Recognition File Number			BP10588
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10 <sup>-5</sup>	2.0
Thermal Conductivity	ASTM C 177		2.0
<b>Flame resistance properties</b>			
Level 2	ASTM E 119		Passed
Level 1	UL 94		HB
Level 2 and above	UL 94		V0
<b>Physical properties</b>			
Density	ASTM D 792	lbs/ft <sup>3</sup>	125
Water Absorption	ASTM D 570	% by wt.	<1.4

### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 30/04/2024 • Release: 20/09/2023

PIM-Version: 395 • PIM-ID: 716641 • PIM-Code: 395-71-6.5.6-7.8-8



	Test method	Unit	Guideline value
Barcol Hardness	ASTM D 2583		50

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc. See correlating profile page for sizing and related information.



#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 30/04/2024 • Release: 20/09/2023

PIM-Version: 395 • PIM-ID: 716641 • PIM-Code: 395-71-6.5.6-7.8-8

Page 2 / 2 (Dates in DD/MM/YYYY)

