

Technical Data Sheet

Durolight® S4

GFK-UP

Typical characteristics

- UV-resistant
- Low thermal conductivity

Typical industries

- Chemical Processing Industry
- Mechanical Engineering Industry
- Oil and Gas
- Pipelines

	Test method	Unit	Guideline value
General properties			
Standard Color			Grey
Maximum Service Temp.		°C	288
Continuous Use Temp.		°C	211
Mechanical properties			
Compressive Strength	Internal*	lbf	100,000+
Density	ASTM D 792	lbs/ft ³	123
Flexural Strength	ASTM D 790	psi	24,000
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	8
Thermal properties			
Subambient Operating Temperature		°C	-165
Thermal Conductivity	ASTM C 177	W / (m * K)	0.3
Flame resistance properties			
UL Subject 94	UL 94		HB
Physical properties			
Water Absorption	ASTM D 570	% by wt.	0.2

*Simulated field test was administered. For more information, including test results, please contact Roechling Industrial Cleveland.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 05/12/2025 • Release: 25/11/2025 • Version: 9.0
 PIM-Version: 102 • PIM-ID: 775482 • PIM-Code: 102-23-15.12-7.5.5.5-3
 Company-IDs: 23050 20000-1

Page 1 / 1 (Dates in DD/MM/YYYY)

