

Technical Data Sheet

Durostone[®] EPM 203

Typical characteristics

- Epoxy (EP) resin matrix reinforced with an e-glass mat
- Good mechanical and electronical properties at both room temperature and elevated temperatures

Typical industries

- Generátory a motory
- Obnovitelné energie
- Elektrotechnický průmysl
- Větrná energie
- Elektrické izolační konstrukční díly
- Hydrogen Energy

	Test method	Unit	Guideline value
Mechanical properties			
Density	ISO 1183	g / cm ³	1,85
Flexural strength [⊥]	ISO 178	MPa	360
Flexural strength [⊥] +150°C	ISO 178	MPa	180
Modulus of elasticity in flexion [⊥]	ISO 178	MPa	20000
Modulus of elasticity in flexion [⊥] +150°C	ISO 178	MPa	15000
Compressive strength [⊥]	ISO 604	MPa	500
Tensile strength II	ISO 527	MPa	280
Impact strength II (Charpy)	ISO 179	kJ / m ²	100
Thermal properties			
Temperature index	IEC 60216	T.I.	180
Insulation class	IEC 60085	/	H
Physical properties			
Water absorption (4mm thickness)	ISO 62	%	0,1
Dielectrical properties			
Electric strength 90°C under oil [⊥]	IEC 60243	kV / mm	13
Electric strength 90°C under oil II	IEC 60243	kV/25mm	70
Specific surface resistance	IEC 60093	Ohm	10 ¹³
Comparative tracking index	IEC 60112	CTI	400

= perpendicular to the lamination II = parallel to the lamination

Röchling Industrial Nancy S.A.S.

8, Rue André Fruchard • 54520 B.P.12, Maxéville/France (FR) • Tel. +33 383 342424
 info@roechling-permali.fr • www.roechling.com/industrial/nancy

Print: 27/04/2024 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 416 • PIM-ID: 710059 • PIM-Code: 416-20-9.8-3.6.11.10.5.9-13

Page 1 / 2 (Dates in DD/MM/YYYY)



The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: www.roechling-industrial.com/gtc



Röchling Industrial Nancy S.A.S.

8, Rue André Fruchard • 54520 B.P.12, Maxéville/France (FR) • Tel. +33 383 342424
info@roechling-permali.fr • www.roechling.com/industrial/nancy

Print: 27/04/2024 • Release: 20/09/2023 • Version: 1.0
PIM-Version: 416 • PIM-ID: 710059 • PIM-Code: 416-20-9.8-3.6.11.10.5.9-13

