

### Technical Data Sheet

## Fibracon<sup>®</sup> PTFE + 15% Carbon

PTFE

#### Typical characteristics

- Low wear when lubricated with water
- Reduced deformation under load (improved compressive strength)
- Improved thermal and electrical conductivity

#### Typical industries

- 화학 가공 산업
- 차량 제조
- 전자 제품
- Oil and Gas
- 기계 공학 산업
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM 1457	g / cm <sup>3</sup>	2.0 - 2.2
<b>Mechanical properties</b>			
Hardness	ASTM 1706	Shore D	58 - 62
Tensile Strength (23°C)	ASTM 1457	MPa	18
Elongation at Break	ASTM 1457*	%	>250
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 11/07/2025 • Release: 20/09/2023

PIM-Version: 34 • PIM-ID: 709605 • PIM-Code: 34-40-16.12.13-7.7.8.5.5.9.5.10-2

Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

