# Röchling

### **Technical Data Sheet**

## Fibracon<sup>®</sup> PTFE + 23% Carbon+ 2% Graphite

PTFE

#### Typical characteristics • Good for dry and poorly

• Electrically conductive

lubricated environments

• Good thermal conductivity

Reduced deformation under

load compared to virgin PTFE

#### **Typical industries**

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering Industry
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Density	ASTM D4894	g / cm <sup>3</sup>	2.09
Mechanical properties			
Hardness	Needle	Shore D	64 - 70
Tensile Strength (23°C)	ASTM D4894	MPa	18
Elongation at Break	ASTM D4894	%	65
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

#### ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 12/07/2025 • Release: 20/09/2023 PIM-Version: 43 • PIM-ID: 709613 • PIM-Code: 43-40-16.3.13.14-7.7.8.5.5.9.5.10-1 Company-IDs: 21220

