

Technical Data Sheet

Fibracon® PTFE + 25% Carbon filled

Product characteristics

- Particularly low wear when lubricated with water
- Reduced deformation under load (improved compressive strength)
- Improved thermal and electrical conductivity

Product industries

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering Industry
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Bulk Density	ASTM D4894	g/l	600
Specific Gravity	ASTM D4894	-	2.10 0.03
Mechanical properties			
Tensile Strength (Cross Direction)	ASTM D4894	MPa	Min.15
Elongation (Cross Direction)	ASTM D4894	%	Min.90
Ball Hardness	ISO 2039	MPa	4502
Deformation Under Load	ASTM D621	%	5 - 7
Thermal properties			
Service Temperature		°C	-200 to +260
Electrical properties			
Volume Resistivity	ASTM D257	Ωcm	10 ⁴

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

Röchling Industrial (UK) Ltd. – High Peak

 $Bowden \ Hey \ Road - Chapel-en-le-Frith \bullet SK23 \ OQZ \ High \ Peak, \ Derbyshire/United \ Kingdom \ (GB) \bullet Tel. + 44 \ 1298 \ 811 \ 800 \ info@roechling-fibracon.co.uk \bullet www.roechling.com/industrial/high-peak$



PIM-Version: 35 • PIM-ID: 709615 • PIM-Code: 35-40-10.8.12-7.6.8.5.5.9.5.10-1

