

Technical Data Sheet

Fibracon[®] PTFE + 25% Carbon filled

Typical characteristics

- Particularly low wear when lubricated with water
- Reduced deformation under load (improved compressive strength)
- Improved thermal and electrical conductivity

Typical industries

- 화학 가공 산업
- 차량 제조
- 전자 제품
- Oil and Gas
- 기계 공학 산업
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Bulk Density	ASTM D4894	g/l	600
Specific Gravity	ASTM D4894	-	2.1±0.03
Mechanical properties			
Tensile Strength (Cross Direction)	ASTM D4894	MPa	Min.15
Elongation (Cross Direction)	ASTM D4894	%	Min.90
Ball Hardness	ISO 2039	MPa	45±2
Deformation Under Load	ASTM D621	%	5 - 7
Thermal properties			
Service Temperature		°C	-200 to +260
Electrical properties			
Volume Resistivity	ASTM D257	Ωcm	10 ⁴

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 10/05/2024 • Release: 20/09/2023

PIM-Version: 35 • PIM-ID: 709615 • PIM-Code: 35-40-10.8.12-7.6.8.5.5.9.5.10-1

Page 1 / 1 (Dates in DD/MM/YYYY)

