Röchling

Industrial

Technical Data Sheet Fibracon[®] PTFE + 25% Ekonol

Product characteristics

- Good wear resistance
- Improved stability and at high temperatures

Product industries

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering
- Industry
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Density	ASTM D1457	g / cm ³	1.8 - 2.0
Mechanical properties			
Hardness	ASTM D1706	Shore D	56 - 60
Tensile Strength (23°C)	ASTM D1457	N/mm ²	>7
Elongation at Break	ASTM D1457*	%	>150
Thermal properties			
Service Temperature		°C	-200 to +260

*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

Röchling Industrial (UK) Ltd. – High Peak Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 29/04/2024 • Release: 20/09/2023 PIM-Version: 37 • PIM-ID: 709616 • PIM-Code: 37-40-142.14-7.6.8.5.5.9.5.10-2