

Technical Data Sheet

Fibracon[®] PTFE + 25% Ekonol

PTFE

Typical characteristics

- Good wear resistance
- Improved stability at high temperatures

Typical industries

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering Industry
- Healthcare
- Food Industry
- Wind Energy

	Test method	Unit	Guideline value
General properties			
Density	ASTM D1457	g / cm ³	1.8 - 2.0
Mechanical properties			
Hardness	ASTM D1706	Shore D	56 - 60
Tensile Strength (23°C)	ASTM D1457	N/mm ²	>7
Elongation at Break	ASTM D1457*	%	>150
Thermal properties			
Service Temperature		°C	-200 to +260

*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/12/2025 • Release: 20/09/2023

PIM-Version: 37 • PIM-ID: 709616 • PIM-Code: 37-40-143.24-7.7.8.5.5.27.5.10-2

Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

